

## **Here's how you can obtain long, satisfactory service from your new Coe Impression Tray.**

### **Handling:**

Coe Impression Trays are constructed of nickel-plated brass. Modification of the tray, if necessary, should be slight and carefully made with finger pressure. **DO NOT USE PLIERS.** *(Note: Excessive manipulation will crack the plating.)*

### **Cleaning:**

To clean your Coe Impression Tray, remove the bulk of the impression material from the tray. Immerse the tray in a solution of Coe Tray Cleaner for 30 minutes. Stubborn particles of alginate may then be removed by lightly brushing with a soft bristle brush. Coe Tray Cleaner and warm water may be used for removal of wax and compound.

### **Sterilizing:**

Coe trays may be autoclaved at 250 degrees Fahrenheit for 30 minutes. Trays should be stored dry.

### **Precautions:**

Do NOT use dry heat sterilization.

The use of various chemical disinfectants/sterilants may cause discoloration and/or etching of trays and therefore is not recommended.

An electrolytic reaction may occur if trays are placed in a liquid medium with dissimilar metals, causing damage to the nickel plating.